



Technical data Sheet

EXCOAT PLASTIC EMULSION

Description:

Rayband's EXCOAT PLASTIC EMULSION is water based exterior wall coating suitable for dry to moderate humid climatic condition. It has excellent weather resistance. It contains special anti fungal additives, which prevents the paint film from fungal attack.

Recommended use:

Rayband's EXCOAT EMULSION is an exterior wall finish that can be applied on all types of exterior cement plasters, asbestos sheets, concrete etc.

Product data:

Covering capacity** : 10 - 12 sq mtrs/liter (single coat)
(On normal masonry surface by brushing).

Drying time (surface drying) : 30 minutes

Shades available : as per requirement.

Shelf- life : 2 years from date of manufacturing
In original tightly closed container
Away From direct sunlight and heat.

** Coverage may vary slightly depending on the surface roughness and method of application.

Recommended thinner: water

Surfaces to be painted:



New or old interior and exterior cement plasters asbestos and concrete.

Method of application:

Brush, Roller

Surface preparation & application:

Surface preparation:

Remove the loose particles of previous coatings completely. Any previous growth of fungus, algae or moss must be thoroughly removed by vigorous wire brushing and cleaning with water.

Freshly plastered walls must be allowed to cure completely for at least 48 hours.

Filling:

Application of any kind of putty is not recommended for exterior surface. For interior surfaces use Rayband's Acrylic wall putty for a smooth finish. Surface imperfections should be suitably filled with cement mixtures.

Priming:

Apply a coat of Rayband's Exterior wall primer by brush/roller by thinning with 15-20% water. Allow the primer to dry for 4 – 5 hours

Finish Coats:

Apply 2 coats of Rayband's Excoat plastic emulsion thinned with water in the ratio of 2:1 by volume (paint to water), with a recoating interval of 4- 5 hours. Over thinning should be avoided as it will affect the performance of the paint.



Safety:

As a general rule avoids contact with eyes. Clean hands with water and soap solution after painting.